

HexTow[®] Carbon Fiber

from Hexcel





HexTow® carbon fiber from Hexcel is produced in a continuous operation in which the polyacrylonitrile precursor undergoes a series of precisely controlled processes. Exposure to extremely high temperatures chemically changes the precursor, yielding high strength-to-weight and high stiffness-to-weight properties through oxidation, carbonization and graphitization. The successive surface treatment and sizing stages improve bonding and handleability. The resulting carbon fiber is stronger than steel, lighter than aluminum and as stiff as titanium. It can be supplied in two basic forms: Continuous Fiber and Chopped Fiber.

HEXCEL STRENGTHS

- Vast aerospace database
 - Extensive military, space and commercial aerospace qualifications
- More than 30 years of carbon fiber manufacturing experience
 - U.S. precursor
- Technology development capability
- Customer technical support

CONTINUOUS FIBER

Continuous fiber can be combined with virtually all the thermoset and thermoplastic resin systems. They are used for weaving, braiding, filament winding applications, uni-directional tapes and prepreg tow for fiber placement.




Typical Product Data

Fiber Type	Number of Filaments	Tensile Strength		Tensile Modulus*		Strain**	Weight/Length	Density	Standard Spool Size
		ksi	MPa	Msi	GPa				
AS2C	3,000	644	4,440	32.0	221	1.9	0.200	1.80	4.0
AS4	3,000	653	4,500	33.5	231	1.8	0.210	1.79	4.0
	6,000	628	4,330	33.5	231	1.8	0.427	1.79	4.0
	12,000	649	4,475	33.5	231	1.8	0.858	1.79	8.0
AS4C	3,000	647	4,460	33.5	231	1.8	0.200	1.78	4.0
	6,000	626	4,320	33.5	231	1.8	0.400	1.78	4.0
	12,000	634	4,370	33.5	231	1.8	0.800	1.78	8.0
AS4D	12,000	689	4,750	35.5	245	1.8	0.765	1.79	8.0
AS7	12,000	700	4,830	35.0	241	1.8	0.800	1.79	8.0
IM2A	6,000	740	5,100	40.0	276	1.7	0.223	1.78	2.0
	12,000	790	5,450	40.0	276	1.8	0.446	1.78	4.0
IM2C	12,000	830	5,720	43.0	296	1.9	0.446	1.78	4.0
IM6	12,000	833	5,740	40.5	279	1.9	0.446	1.76	8.0
IM7	6,000	770	5,310	40.0	276	1.8	0.223	1.78	2.0
	12,000	822	5,670	40.0	276	1.9	0.446	1.78	4.0
IM9	12,000	890	6,140	44.0	304	1.9	0.335	1.80	2.0
PV42/850	12,000	846	5,830	42.0	292	1.9	0.446	1.79	6.0

* Tensile Modulus Calculated as Secant (6000 - 1000)

** Strain at Failure

Strength vs Modulus



Typical Epoxy Composite Properties*

Property	IM7 12k		AS4 12k	
	US Units	SI Units	US Units	SI Units
0° Tensile Strength	395 ksi	2723 MPa	320 ksi	2205 MPa
0° Tensile Modulus	23.8 Msi	164 GPa	20.5 Msi	141 GPa
0° Tensile Strain	1.62%	1.62%	1.55%	1.55%
0° Flexural Strength	270 ksi	1862 MPa	274 ksi	1889 MPa
0° Flexural Modulus	22.0 Msi	152 GPa	18.4 Msi	127 GPa
0° Short Beam Shear Strength	19.9 ksi	137 MPa	18.5 ksi	128 MPa
0° Compressive Strength	245 ksi	1689 MPa	222 ksi	1530 MPa
0° Compressive Modulus	21.7 Msi	150 GPa	18.6 Msi	128 GPa
90° Tensile Strength	16.1 ksi	111 MPa	11.7 ksi	81 MPa
Fiber Volume	60%	60%	60%	60%

* Hexcel 350°F Epoxy Resin System, Room Temperature, Dry Test Results

Available Sizing for HexTow® Continuous Carbon Fiber Products

Designation	Fiber Out-Life	Size Compatibility**	Recommended Uses	Sizing Level
G	12 months	Epoxy, Phenolic, Polycarbonate, Polyurethane, Polysulfones	Weaving Prepreg Tape	0.8 - 1.2 0.2 - 0.4
GP	Indefinite	Epoxy, Phenolic, Vinyl Ester	Weaving & Filament Winding Prepreg Tape	0.8 - 1.2 0.2 - 0.4
H	Indefinite	Epoxy	Weaving	0.8 - 1.2
R	Indefinite	Epoxy, Polyester	Filament Winding	1.2 - 1.6
GS	36 months	Epoxy, Vinyl Ester, Polyurethane	Prepreg Tape	0.3 - 0.7
E	Indefinite	Epoxy	Prepreg Tape, Weaving, Pultrusion & Filament Winding	0.9 - 1.3
J	Indefinite	Epoxy	Weaving	0.8 - 1.2

** Compatibility with these Matrices is considered theoretically compatible. Hexcel cannot guarantee their results.

CHOPPED FIBER

Chopped fiber is used in compression and injection molding compounds to produce machine parts, gears and chemical valves. The finished products have excellent corrosion, creep and fatigue resistance, plus high strength and stiffness characteristics.



HexTow® Chopped Carbon Fiber Products

		Fiber Type			
Property	Units	1	2	3	4
IM Carbon Fiber	%	100	50 - 100	0 - 100	0
AS Carbon Fiber	%	0	0 - 50	100 - 0	100
Fiber Length*	in.	0.25	0.25	0.25	0.25
	mm	6.4	6.4	6.4	6.4
Standard Packaging	lbs	40	40	40	40
	kg	18.1	18.1	18.1	18.1

* Other fiber lengths available on request

Available Sizing for HexTow® Chopped Carbon Fiber Product

Sizing Type	Units	XX00	XX25	BR102
Sizing Content	wt. %	3 - 7%	3 - 7%	4 - 8%
Size Compatibility**		Polyamide (nylon)	Polyamide (nylon), Polycarbonate, Polyphenylene Sulfide, Polyurethane, PEI, Polyester	Polycarbonate, Polysulfone, Epoxy

** Compatibility with these Matrices is considered theoretically compatible. Hexcel cannot guarantee their results.



Important

Hexcel Corporation believes, in good faith, that the technical data and other information provided herein is materially accurate as of the date this document is prepared. Hexcel reserves the right to modify such information at any time. The performance values in this data sheet are considered representative but do not and should not constitute specification minima. The only obligations of Hexcel, including warranties, if any, will be set forth in a contract signed by Hexcel or in Hexcel's then current standard Terms and Conditions of Sale as set forth on the back of Hexcel's Order Acknowledgement.

For More Information

Hexcel is a leading worldwide supplier of composite materials to aerospace and other demanding industries. Our comprehensive product range includes:

- Carbon Fiber
- RTM Materials
- Honeycomb Cores
- Carbon, Glass, Aramid and Hybrid Prepregs
- Structural Film Adhesives
- Honeycomb Sandwich Panels
- Engineered Core
- Reinforcement Fabrics

For U.S. quotes, orders and product information call toll-free 1-866-556-2662 or 1-800-987-0658.

For other worldwide sales office telephone numbers and a full address list please visit:

<http://www.hexcel.com/contact/salesoffices>.