



5353

Aramid and High Performance Fabrics

Product Data

STYLE 5353

US System

Type of Yarns **Warp Yarn:** Twaron 2200 1270 Dtex.
Fill Yarn: Twaron 2200 1270 Dtex.

Fabric Weight, Dry 5.0 oz/yd²
170 g/m²

Weave Style Crowfoot

CONSTRUCTION

Nominal Construction **Warp Count:** 17
(Yarns/inch) **Fill Count:** 17

Fabric Thickness 9.0 mils
0.23 mm

Yarn Tensile **Warp** 623 lbs.
Filling 635 lbs.

Markets Aeronautics/Aerospace

Applications Aircraft Advanced Composites

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



1913 N. King
Seguin, TX 78155
USA
Phone: 830.401.8180
Fax: 830.379.9544

3, Avenue Condorcet
69608 Villeurbanne Cedex
France
Phone: 33 4 72 44 40 00
Fax: 33 4 78 89 72 30