



388

Aramid and High Performance Fabrics

Product Data

STYLE 388

| | | |
|----------------------|------------------|------------------------|
| Type of yarns | <i>Warp Yarn</i> | Kevlar 49, 1420 denier |
| | <i>Fill Yarn</i> | Kevlar 49, 1420 denier |

| | | |
|----------------------|------|-----------------------|
| Fabric Weight | 15.0 | (oz/yd ²) |
| | 508 | (g/m ²) |

| | |
|--------------------|------------|
| Weave Style | Basket 8x8 |
|--------------------|------------|

CONSTRUCTION

| | | |
|--|-------------------|----|
| Nominal Construction yarns/inch | <i>Warp Count</i> | 40 |
| | <i>Fill Count</i> | 40 |

| | | |
|-------------------------|------|--------|
| Fabric Thickness | 26.0 | (mils) |
| | 0.66 | (mm) |

| | | |
|--------------------------|------|----------|
| Breaking Strength | 1830 | (lbf/in) |
| | 1790 | (lbf/in) |

| | |
|----------------|--|
| Markets | <i>Aeronautics/Aerospace, Recreational</i> |
|----------------|--|

| | |
|---------------------|--|
| Applications | <i>Low Pressure Composites, Aircraft Advanced Composites</i> |
|---------------------|--|

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



2200 S. Murray Ave.
P.O. Box 2627
Anderson, SC 29622
Phone: 864.225.7028
Fax: 864.260.6581

580 North Gilbert St.
Fullerton, CA 92833
Phone: 714.278.0850
Fax: 714.526.2367