



383

Aramid and High Performance Fabrics

Product Data

STYLE 383

US System

Type of Yarns **Warp Yarn:** Kev. 49, 2160 Den.
Fill Yarn: Kev. 49, 2160 Den.

Fabric Weight, Dry 9.0 oz/yd²
305 g/m²

Weave Style 5 Harness Satin

CONSTRUCTION

Nominal Construction **Warp Count:** 16
(Yarns/inch) **Fill Count:** 16

Fabric Thickness 13.0 mils
.33 mm

Yarn Tensile **Warp** 104 lbs.
Filling 104 lbs.

Markets Recreational

Applications Low Pressure Composites

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



1913 N. King
Seguin, TX 78155
USA
Phone: 830.401.8180
Fax: 830.379.9544

580 North Gilbert St.
Fullerton, CA 92833
USA
Phone: 714.278.0850
Fax: 714.526.2367

3, Avenue Condorcet
69608 Villeurbanne Cedex
France
Phone: 33 4 72 44 40 00
Fax: 33 4 78 89 72 30