



# 5352

## Aramid and High Performance Fabrics

### Product Data

**STYLE 5352**

**US System**

**Type of Yarns**                      **Warp Yarn:**                      Twaron 2200 1270 Dtex.  
**Fill Yarn:**                      Twaron 2200 1270 Dtex.

**Fabric Weight, Dry**                      5.0 oz/yd<sup>2</sup>  
170 g/m<sup>2</sup>

**Weave Style**                      Plain

### CONSTRUCTION

**Nominal Construction**                      **Warp Count:**                      17  
**(Yarns/inch)**                      **Fill Count:**                      17

**Fabric Thickness**                      10.0 mils  
0.25 mm

**Yarn Tensile**                      **Warp**                      624 lbs.  
**Filling**                      643 lbs.

**Markets**                      Aeronautics/Aerospace

**Applications**                      Aircraft Advanced Composites

### IMPORTANT

*All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory and minimum order quantities may apply.*

### FOR FURTHER INFORMATION, PLEASE CONTACT US



1913 N. King  
Seguin, TX 78155  
USA  
Phone: 830.401.8180  
Fax: 830.379.9544

3, Avenue Condorcet  
69608 Villeurbanne Cedex  
France  
Phone: 33 4 72 44 40 00  
Fax: 33 4 78 89 72 30