



Document No.: NMS 191/2 Rev A, April 20th, 2026

NCAMP Material Specification

*This specification is generated and maintained in accordance with NCAMP
Standard Operating Procedures, NSP 100*

350°F Autoclave Cure, High Residual Compression Strength Epoxy Prepregs
Type 40, Class 2, Grade 145, Style 6K-PW ZB

Hexcel M91/IM8-GP 6K PW ZB Fabric

Prepared by: Jonathan John (NCAMP/NIAR) and Vinsensius Tanoto (NCAMP/NIAR)

Reviewed by: Campbell Fritschner (Archer), Michelle Man (NCAMP/NIAR), Austin Gilbert
(Hexcel), Erin Goodman (Hexcel), Royal Lovingfoss (NCAMP/NIAR), Ed Hooper
(NCAMP AER)

Distribution Statement A. Approved for public release; distribution is unlimited.

REVISIONS:

Rev	By	Date	Pages Revised or Added
-	Jonathan John	10/14/2025	Initial release
A	Vinsensius Tanoto and Jonathan John	4/20/2026	Pg 3 and 4: Table 1: Specification limits were revised and added for: ▪ RC - added individual value and tolerances for both, 3% ind. and 2% avg. ▪ FAW - added individual value and tolerances for both, 7% ind. and 5% avg. ▪ VC – updated max average to 2.5% ▪ Flow – updated range 10 to 25 wt % ▪ Gel time - updated range 8 to 30 mins ind. ▪ Tack – Updated pass criteria per NMS levels callout ▪ DSC – spec limits were added ▪ Notes 6, 7 and 9 were removed Pg.4: Section 3.2.2, removed reference to NMS 818/8 and added reinforcement specifications. Pg 5: Section 3.4.4, removed the weight requirement for a single roll of prepreg. Pg. 5 and 6, Updated Table 3 and 4 with spec limit values. Note 4 on table 3 updated to reflect the data computation approach with qualification and historical data.

1. SCOPE:

1.1 Form:

This detail specification along with the base specification NMS 191 establishes the requirements for carbon fiber fabric impregnated with a modified B-staged epoxy resin ("fabric prepreg"). The prepreg is produced using a hot-melt process.

This detail specification follows the section and table numbering scheme of the base specification. It contains additional or superseding requirements. The base specification shall govern where no additional requirement is specified; in such cases, the applicable sections are omitted from this detail specification.

1.2 Classification: All products qualified to this detail specification have the following classification: Type 40, Class 2, Grade 145, Style 6K-PW ZB

3. TECHNICAL REQUIREMENTS:

Table 1 – Prepreg Physical and Chemical Properties

Property	Test Method ⁽¹⁾	Number of Replicates	Requirements ⁽⁵⁾
Resin Content	ASTM D3529	Every roll ⁽²⁾	40 ± 3% ind. 40 ± 2% avg.
Fiber Areal Weight	ASTM D3529	Every roll ⁽²⁾	145 ± 7 gsm ind. 145 ± 5 gsm avg.
Volatile Content	ASTM D3530	First and last rolls of every batch ⁽²⁾	2.5% max avg.
Flow	ASTM D3531	First and last rolls of every batch ⁽²⁾	10 to 25 wt %
Gel Time ⁽⁴⁾	ASTM D3532	First and last rolls of every batch	8 to 30 mins
Tack	Section 4.6.1 of base spec	First and last rolls of every batch	Level IV, V or VI
Drape	Section 4.6.2 of base spec	First and last rolls of every batch	Pass
HPLC ⁽³⁾	SACMA SRM 20R-94	First and last rolls of a batch	Per PCD
FTIR ⁽³⁾⁽⁴⁾	ASTM E168 ASTM E1252	First and last rolls of a batch	Per PCD
Differential Scanning Calorimetry (DSC)			
Exotherm peak temp.	ASTM D3418	First and last rolls of every batch	255 ± 10 °C ⁽⁶⁾
Total heat of reaction	ASTM D3418	First and last rolls of every batch	175 ± 35 J/g ⁽⁶⁾

- (1) Specific procedures should be identical to those used in the original material qualification program.
- (2) Three specimens should be taken across the width of the prepreg; left, center, right.
- (3) Not required for receiving inspection test.
- (4) Optional for batch release test.
- (5) "ind." refers to individual measurements. "avg." refers to the average measurements per roll.
- (6) Product Form is Prepreg.

3.2 Constituent Material Requirements:

3.2.1 Epoxy Resin System: Up to 50% resin blending is allowed.

3.2.2 Reinforcement:

The fabric weaving is controlled through prepreg PCD and NRP 101.

Carbon fiber will be provided per the prepregger's carbon fiber procurement specification and approved PCD. In addition, the following change control is implemented on the carbon fiber.

Efforts to qualify the carbon fiber to NCAMP carbon fiber material specification, NMS 818, are ongoing. In the meantime, Hexcel will continue to provide aerospace-grade carbon fiber for this prepreg per the prepregger's carbon fiber procurement specification HS-CP-5000 and Hexcel's internal aerospace-grade PCD. In addition, the following change control is implemented on the carbon fiber:

The carbon fiber tow product manufacturer shall establish control factors which will yield product meeting the technical requirements of this prepreg specification. The factors which are used in the production of fiber tow used in the prepreg material qualification shall constitute the approved factors; they shall be used for manufacturing production carbon fiber tow product. Control factors are Controlled Process Equipment and Controlled Process Parameters for producing the product. Control factors include, but are not limited to, the following:

- a) PAN Precursor formulation (raw ingredients and ratios),
- b) PAN Precursor manufacturing process, equipment, line, or site,
- c) PAN Precursor acceptance requirements,
- d) Carbon fiber tow processing parameters (e.g. temperature and speed),
- e) Carbon fiber tow manufacturing equipment, line, or site,
- f) Carbon fiber tow acceptance requirements,
- g) Carbon fiber tow acceptance test methods,
- h) Carbon fiber tow acceptance sampling plan,
- i) Carbon fiber tow surface treatment methods and levels,
- j) Carbon fiber tow sizing formulation and sizing level, and
- k) Carbon fiber tow sizing application and drying methods, including equipment.

If it is necessary to make any change in the above control factors, the carbon fiber tow product manufacturer shall submit for re-approval to NCAMP through the prepreg manufacturer in accordance with NRP 101 Prepreg Process Control Document (PCD)

Preparation and Maintenance Guide. NRP 102 Polyacrylonitrile-based Carbon Fiber Process Control Document (PCD) Preparation and Maintenance Guide may be used as a reference. The change shall not be incorporated prior to the receipt of re-approval notice, typically in the form of a signed Advanced Change Notice (ACN).

3.4 Visual and Dimensional Requirements:

3.4.4 Roll characteristics - The standard width for this product is 60 inches. Other widths may be supplied only if it is specifically requested by the purchaser.

3.5 Laminate (Cured Prepreg) Requirements:

3.5.2 Cured Laminate Physical Properties:

TABLE 3 - Cured Laminate Physical Properties

Property	Test Method ⁽¹⁾	Requirements ⁽²⁾
Cured Ply Thickness, CPT ⁽³⁾	SACMA SRM 10R-94	0.0057 to 0.0065 inch, avg.
Dry Glass Transition Temperature Dry, Tg by DMA ⁽⁴⁾	ASTM D7028	369.9 to 405.9 °F, ind. ⁽⁵⁾ 187.7 to 207.7 °C, ind. ⁽⁵⁾

(1) Specific procedures should be identical to those used in the original material qualification program.

(2) "ind." refers to individual measurements. "avg." refers to the average measurements per panel.

(3) Cured Ply Thickness of the Laminates in Table 4. Computed from actual qualification panel thicknesses using $\alpha=0.01$ and modified CV, and theoretical Cured Ply Thickness as the nominal.

(4) Limits computed from average of qualification data and batch release historical data ± 18 °F.

(5) Dry Tg can be reported in either °F or °C.

3.5.3 Cured Laminate Mechanical Properties:

TABLE 5 - Required Cured Laminate Tests for Mechanical Properties (Class 2)

Property	Test Method ⁽¹⁾	Requirements ⁽³⁾
0° (Warp) Tension Strength and Modulus, Room Temperature, Ambient Layup: [0] ₁₅	ASTM D3039	Strength ⁽²⁾ : Min. Ind. $\geq$ 145.5 ksi Strength ⁽²⁾ : Average $\geq$ 166.1 ksi Modulus ⁽²⁾ : 10.8 to 12.6 Msi, avg
90° (Fill) Compression Strength and Modulus, Room Temperature, Ambient Layup: [90] ₁₅	ASTM D6641	Strength ⁽²⁾ : Min. Ind. $\geq$ 84.94 ksi Strength ⁽²⁾ : Average $\geq$ 100.5 ksi Modulus ⁽²⁾ : 9.8 to 11.4 Msi, avg
0° Short Beam Strength, Room Temperature, Ambient Layup: [0] ₂₄	ASTM D2344	Strength: Min. Ind. $\geq$ 10.9 ksi Strength: Average $\geq$ 12.5 ksi

(1) Specific procedures should be identical to those used in the original material qualification program.

(2) Normalize the properties to a cured ply thickness value of 0.0061 inch, based on theoretical nominal CPT, using the following equation:

$$\text{Normalized_Value} = \text{Measured_Value} \times \text{Measured_CPT} / \text{Nominal_CPT}$$

(3) "ind." refers to individual measurements. "avg." refers to the average of 5 replicates. Limits computed at $\alpha=0.01$ and modified CV.

QUALIFIED PRODUCTS LIST

Supplier Product Designation	Supplier Name and Production Location	Date Qualified	Specification Callout ⁽¹⁾
Hexcel M91/IM8-GP 6K PW ZB	Supplier Name: Hexcel Salt Lake City Plant Production Location: 6700 West 5400 South West Valley City, UT 84118, USA Line #: 2 and 15	04/20/2026	NMS 191/2 Classification callout is optional because Type 40, Class 2, Grade 145 is the only classification allowed in this QPL.

⁽¹⁾ In accordance with NCAMP Standard Operating Procedures, NSP 100, this QPL shall not contain alternate materials/products. Additional production location may be included in the QPL only after successful equivalency demonstration and approval per NCAMP Prepreg Process Control Document (PCD) Preparation and Maintenance Guide, NRP 101.

⁽¹⁾ The proper specification callout for material procurement purpose is "NMS 191/2." This specification is developed based on the material properties that are available publicly. The purchaser may specify additional requirements beyond those specified in this specification, especially when the purchaser has generated additional material properties beyond those available publicly or when the application requires additional requirements. The additional requirements are subject to supplier review and approval.